

Amendment After Allowance under 37 CFR 1.312

Date filed September 15, 2006

U.S. Patent Application Serial No. 10/735,886

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1 Claim 1 (Currently Amended): A multilayer interconnection structure, comprising:

2 a first interconnection layer including a copper interconnection pattern, said copper
3 interconnection pattern having a top principal surface coincident to a top principal surface of said first
4 interconnection layer and filling a hole formed in said first interconnection layer;

5 an interlayer insulation film formed on said first interconnection layer;

6 a second interconnection layer formed on said interlayer insulation film;

7 a via-hole formed in said interlayer insulation film so as to expose said copper interconnection
8 pattern; and

9 a tungsten plug formed in said via-hole and said hole so as to connect said first interconnection
10 layer and said second interconnection layer electrically,

11 said via-hole having a depth/diameter ratio of 1.25 - 3.0,

12 wherein there is formed a conductive nitride film between an outer wall of said tungsten plug and
13 an inner wall of said via-hole such that said conductive nitride film is defined by an inner wall contacting
14 with said outer wall of said tungsten plug and an outer wall contacting with said inner wall of said via-
15 hole,

16 said conductive nitride film being formed of a first nitride film and a second nitride film stacked

Amendment After Allowance under 37 CFR 1.312

Date filed **September 15, 2006**

U.S. Patent Application Serial No. **10/735,886**

17 inside said first nitride film, said first nitride film having an outer surface and an inner surface, said outer
18 surface of said first nitride film being in intimate contact with said inner wall of said via-hole, said second
19 nitride film having an outer surface and an inner surface, said outer surface of said second nitride film
20 being in intimate contact with said inner surface of said first nitride film, said inner surface of said second
21 nitride film being in intimate contact with said outer surface of said tungsten plug.

Claims 2 and 3 (Canceled).

1 Claim 4 (Previously Presented): The multilayer interconnection structure as claimed in claim
2 1, wherein said first nitride film is formed of a TaN film and said second nitride film is formed of a TiN
3 film.

1 Claim 5 (Previously Presented): The multilayer interconnection structure as claimed in claim 1,
2 wherein said nitride film has a composition with characteristics of being corrosion resistant to a fluoride
3 gaseous source of tungsten, said fluoride gaseous source of tungsten forming said tungsten plug.

1 Claim 6 (Original): The multilayer interconnection structure as claimed in claim 1, wherein said
2 second interconnection layer contains an aluminum interconnection pattern.

Amendment After Allowance under 37 CFR 1.312

Date filed **September 15, 2006**

U.S. Patent Application Serial No. **10/735,886**

1 Claim 7 (Withdrawn): A method of forming a multilayer interconnection structure, comprising
2 the steps of:

3 forming an interlayer insulation film on a first interconnection layer including a copper
4 interconnection pattern;

5 forming a via-hole in said interlayer insulation film so as to expose said copper interconnection
6 pattern;

7 introducing a substrate carrying thereon said first interconnection layer and said interlayer
8 insulation film into a reactive sputtering apparatus and forming a nitride film on said interlayer insulation
9 film by a reactive sputtering process, such that said nitride film covers an inner wall surface of said via-
10 hole;

11 forming a tungsten plug, after said step of forming said nitride film, on said interlayer insulation
12 film such that said tungsten plug fills said via-hole; and

13 forming a second interconnection layer, after said step of forming said tungsten plug, on said
14 interlayer insulation film,

15 wherein there are provided, after said step of forming said nitride film but before said step of
16 forming said tungsten plug, the steps of:

17 isolating said substrate from a sputtering target provided in said reactive sputtering apparatus; and

18 cleaning a surface of said sputtering target, after said step of forming said nitride film, in said
19 reactive sputtering apparatus in a state in which said substrate is isolated from said sputtering target.

Amendment After Allowance under 37 CFR 1.312

Date filed **September 15, 2006**

U.S. Patent Application Serial No. **10/735,886**

1 Claim 8 (Withdrawn): The method as claimed in claim 7, wherein said cleaning step is
2 conducted such that a nitride film on said sputtering target is removed and the surface of a metal
3 constituting said sputtering target is exposed

1 Claim 9 (Withdrawn): The method as claimed in claim 8, wherein said cleaning step is finished,
2 after said surface of said metal is exposed at said sputter target surface, by conducting a reactive sputtering
3 process of a nitride film.

1 Claim 10 (Withdrawn): The method as claimed in claim 7, wherein said step of isolating said
2 substrate is conducted by taking out said substrate out of said reactive sputtering apparatus.

1 Claim 11 (Withdrawn): The method as claimed in claim 10, wherein said sputtering apparatus
2 forms a single-wafer processing apparatus together with a vacuum transportation chamber coupled to said
3 sputtering apparatus and further with another processing chamber coupled to said vacuum transportation
4 chamber, and wherein said step of taking out said substrate out of said sputtering apparatus comprises a
5 step of transporting said substrate from said another processing chamber via said vacuum transportation
6 chamber.

1 Claim 12 (Withdrawn): The method as claimed in claim 11, wherein said another processing
2 chamber is a CVD chamber used for forming a tungsten film.

Amendment After Allowance under 37 CFR 1.312

Date filed **September 15, 2006**

U.S. Patent Application Serial No. **10/735,886**

1 Claim 13 (Withdrawn): The method as claimed in claim 7, wherein said step of isolating said
2 substrate comprises a step of introducing a shutter inside said reactive sputtering apparatus between said
3 substrate and said sputtering target.

1 Claim 14 (Withdrawn): The method as claimed in claim 7, wherein said step of introducing said
2 nitride film comprises a step, after introducing said substrate into said reactive sputtering apparatus but
3 before exciting plasma, of introducing a nitrogen gas to a surface of said substrate.

1 Claim 15 (Withdrawn): The method as claimed in claim 7, wherein said step of forming said
2 tungsten plug is conducted by a CVD process using a fluoride gaseous source of tungsten so as to fill said
3 via-hole by a tungsten film via said nitride film, and wherein said step of filling said via-hole by said
4 tungsten film is conducted while supplying a hydrogen gas to a surface of said substrate.

1 Claim 16 (Withdrawn): The method as claimed in claim 7, wherein said step of forming said
2 tungsten plug comprises the steps of: forming a passivation film of tungsten on said nitride film covering
3 said inner wall surface of said via hole, by supplying a gaseous source of tungsten and a reactive gas
4 decomposing said fluoride gaseous source to a surface of said via-hole alternately with an intervening
5 purging process; and depositing a tungsten film on said passivation film by a CVD process, wherein at
6 least said step of forming said passivation film is conducted while supplying a hydrogen gas to a surface

Amendment After Allowance under 37 CFR 1.312

Date filed **September 15, 2006**

U.S. Patent Application Serial No. **10/735,886**

of said substrate.

Claim 17 (Withdrawn): The method as claimed in claim 7, wherein said step of forming said tungsten plug comprises the step of processing a surface of said via hole, before deposition of said tungsten film, by plasma of a gas containing hydrogen.

Claim 18 (Currently Amended): A semiconductor device, comprising:

- a substrate; and
- a multilayer interconnection structure formed on said substrate, said multilayer interconnection structure comprising:
 - a first interconnection layer including a copper interconnection pattern, said copper interconnection pattern having a top principal surface coincident to a top principal surface of said first interconnection layer and filling a hole formed in said first interconnection layer;
 - an interlayer insulation film formed on said first interconnection layer;
 - a second interconnection layer formed on said interlayer insulation film;
 - a via-hole formed in said interlayer insulation film so as to expose said copper interconnection pattern; and
 - a tungsten plug formed in said via-hole and said hole so as to connect said first interconnection layer and said second interconnection layer electrically,
 - said via-hole having a depth/diameter ratio of 1.25 - 3.0,

Amendment After Allowance under 37 CFR 1.312

Date filed **September 15, 2006**

U.S. Patent Application Serial No. **10/735,886**

15 wherein there is formed a conductive nitride film between an outer wall of said tungsten plug and
16 an inner wall of said via-hole such that said conductive nitride film is defined by an inner wall contacting
17 with said outer wall of said tungsten plug and an outer wall contacting with said inner wall of said via-
18 hole,

19 said conductive nitride film being formed of a first nitride film and a second nitride film stacked
20 inside said first nitride film, said first nitride film having an outer surface and an inner surface, said outer
21 surface of said first nitride film being in intimate contact with said inner wall of said via-hole, said second
22 nitride film having an outer surface and an inner surface, said outer surface of said second nitride film
23 being in intimate contact with said inner surface of said first nitride film, said inner surface of said second
24 nitride film being in intimate contact with said outer surface of said tungsten plug.

* * * *